

## CLAIMS

1. An interlayer film for a laminated glass,  
which contains a matrix resin, a liquid plasticizer,  
5 acetyl acetone, alkali metal and at least one kind of metal  
selected from the group consisting of magnesium and  
alkaline earth metal, the content of the alkali metal being  
20 to 120 ppm, the content of at least one kind of metal  
selected from the group consisting of magnesium and  
10 alkaline earth metal being 15 ppm or more and less than 60  
ppm, and the content of the acetyl acetone being 0.008  
parts by weight or more with respect to 100 parts by weight  
of the matrix resin.
- 15 2. The interlayer film for a laminated glass  
according to Claim 1,  
wherein at least one kind of metal selected from the  
group consisting of magnesium and alkaline earth metal is  
magnesium.
- 20 3. A laminated glass,  
which has the interlayer film for a laminated glass  
according to Claim 1 or 2 and two glass plates supporting  
the interlayer film for a laminated glass by sandwiching,  
25 and has a metal coating layer in at least one interface of  
two interfaces between the interlayer film for a laminated  
glass and the glass plates.